

TECHNICAL SHEET OF CONFORMITY EN 13707 - EN 13969

Product	NORDSTABIL MM 3	0101GC054M30FS0017A
Family	BPP0302	
Carrier	Composit polyester	
Compound	Plastomeric bitumen membrane	

Backing	PE FILM <input checked="" type="checkbox"/>	SAND <input checked="" type="checkbox"/>	SLATE GRANULES <input type="checkbox"/>	PP FILM <input type="checkbox"/>	OTHER <input type="checkbox"/>
Use	SINGLE LAYER <input type="checkbox"/>	BASEMENT <input checked="" type="checkbox"/>	TOP LAYER <input type="checkbox"/>	UNDERLAY <input checked="" type="checkbox"/>	UNDER HEAVY PROTECTION ROOF GARDENS <input type="checkbox"/>

Method of application	TORCH <input checked="" type="checkbox"/>	GLUE <input type="checkbox"/>	HOT AIR <input type="checkbox"/>	MECHANICALLY FIXING <input type="checkbox"/>	SELFADHESIVE <input type="checkbox"/>
------------------------------	---	-------------------------------	----------------------------------	--	---------------------------------------

NOTE : Apply a reflecting paint (except differently specified) on the surface of plastomeric bitumen membranes without mineral granules. to protect them when used as a single layer or toplayer exposed
 For a correct use of the product always check Nord Bitumi Technical Manual

CHARACTERISTIC	TEST METHOD	UNITS	TOLLERANCE	VALUE
Length/Width	EN 1848-1	m	MLV	10,0-1% / 1,0-1%
Visible defects	EN 1850-1	Visual		None
Thickness	EN 1849-1	mm	MDV - 0,2 mm	3,0
Straightness	EN 1848-1	mm/10 m	MLV	< 20
Watertightness at 60KPa	EN 1928 - B	Kpa		Pass
External fire performance	EN 13501 - 5			F Roof
Reaction to fire	EN 13501 - 1	Class		F
Tensile strength (L / T)	EN 12311 - 1	N/50mm	MDV - 20%	700 550
Elongation (1) (L/T)	EN 12311 - 1	%	MDV - 15	40 40
Resistance to tearing (2) (L/ T)	EN 12310 - 1	N	MDV - 30%	200 200
Dimensional stability (L)	EN 1107 - 1	%	MLV	-0,3
Flexibility at low temperature	EN 1109	°C	MLV	-10
Flow resistance < 2mm	EN 1110	°C	MLV	+120°
Joint strength (shear resistance)	EN 12317 - 1	N/50mm	MDV - 20%	600 450
Resistance to impact	EN 12691	mm	MLV	900
Resistance to static loading	EN 12730	Kg	MLV	15
Durability after ageing	EN 1296/1928	Kpa		NPD
Chemical resistance	EN 1847/1928	Kpa		NPD

1) For membranes reinforced with fiberglass : MDV - 2 absolut
 2) For membranes reinforced with fiberglass : NPD (no performance determined)
 Water vapour properties (EN 1931) : If the factor μ is not determined, a value of 20,000 may be used for calculation purposes
 MDV = manufacturer's declared value
 MLV = manufacturer's limiting value

DANGEROUS SUBSTANCES : according to the Italian law "Ministerial decree n°65 of 14.03.2003 the product does not contain dangerous substances, the release of a safety data sheet is not mandatory
 Upon request Nord Bitumi may send an informative data sheet for a correct use of the product.

NORD BITUMI SPA
 Via Campagnola 8
 37060 Sona Loc. Valle (VR)

Rev.	Date
01	01/09/2006

Date
12/10/2006

M.03.05 Rev. 01